

# **Wide Angle Diffusers**

## PoG Diffuser 45x40



#### **Features and Advantages**


The PoG (Polymer on Glass) diffuser combines a micro-structured polymer layer on a glass substrate, offering wide wavelength coverage (450–2000 nm), high transmission (>90%), customizable divergence angles (10°–130°) with various beam shapes, and excellent thermal stability (–40 °C to 125 °C, reflow soldering up to 260 °C), making it a cost-effective, reliable, and scalable solution for VCSEL-based applications such as 3D sensing, LiDAR, incabin monitoring, robotics, and machine vision.

#### **Product Specifications**

Product Code		120206000555 (1)
Specification Data	Unit	
Typical FOI Angle (FWHM) Horizontal (2)(3)	0	45
Typical FOI Angle (FWHM) Vertical (2)(3)	٥	40
Material		Epoxy on glass
Length (L)	mm	$3.32 \pm 0.03$
Width (W)	mm	$3.32 \pm 0.03$
Thickness (T)	mm	$0.384 \pm 0.025$
Clear Aperture (Al x Aw)	mm²	2.190 x 2.126
Design Wavelength (4)	nm	940nm / 850nm
AR Coating (5)	nm	uncoated
Transmission (6)	%	90

<sup>(1)</sup> Example for customization — design, dimensions and coating on request.

### **Product Drawing (mm)**



•

 $<sup>^{(2)}</sup>$  Angle at 50% level normalized to the centroid. Based on radiant intensity.


<sup>(3)</sup> Typical VCSEL under typical driving conditions. Different VCSEL sources or different driving conditions could lead into different FOI values.


 $<sup>^{(4)}</sup>$  Optimization design based on VCSEL@940nm, can also be used for 850nm.

<sup>(5)</sup> Optional for customized AR coating on glass surface.


<sup>(6)</sup> Transmission is 90% for uncoated, and will be 94% with AR coating on glass surface.








Radiant Intensity Distribution Pattern (Left) and Radiant Intensity Output Profile (Right)





Irradiance Distribution Pattern (Left) and Irradiance Output Profile (Right)

 $<sup>\</sup>ensuremath{^{(7)}}$  Simulation based on measurements of a typical module product.